

LIDT TEST RESULTS

LIDT VALUE

10^6 -on-1	$0.941^{+0.043}_{-0.043} \text{ J/cm}^2$
--------------	--

CHARACTERISTIC DAMAGE CURVE

Table 1: Estimated LIDTs from fitting model for sample P2.

Test mode	Threshold (Catastrophic)	Threshold (Color mode)
1-on-1	$1.276^{+0.059}_{-0.058} \text{ J/cm}^2$	-
10-on-1	$1.158^{+0.053}_{-0.052} \text{ J/cm}^2$	-
10^2 -on-1	$1.090^{+0.048}_{-0.048} \text{ J/cm}^2$	-
10^3 -on-1	$1.090^{+0.048}_{-0.048} \text{ J/cm}^2$	$1.068^{+0.048}_{-0.047} \text{ J/cm}^2$
10^4 -on-1	$1.064^{+0.039}_{-0.039} \text{ J/cm}^2$	$1.051^{+0.047}_{-0.047} \text{ J/cm}^2$
10^5 -on-1	$1.006^{+0.045}_{-0.045} \text{ J/cm}^2$	$0.984^{+0.045}_{-0.044} \text{ J/cm}^2$
10^6 -on-1	$0.963^{+0.044}_{-0.044} \text{ J/cm}^2$	$0.941^{+0.043}_{-0.043} \text{ J/cm}^2$




Figure 2. Characteristic damage curve.