

LIDT TEST RESULTS

LIDT VALUE

 10^6-on-1
 $0.359^{+0.048}_{-0.047} \text{ J/cm}^2$

CHARACTERISTIC DAMAGE CURVE

Table 1: Estimated LIDTs from fitting model for sample CAM26_4H_1.

Test mode	Threshold (Catastrophic)	Threshold (Color mode)
1-on-1	$0.928^{+0.123}_{-0.119} \text{ J/cm}^2$	$0.870^{+0.116}_{-0.113} \text{ J/cm}^2$
10-on-1	$0.737^{+0.111}_{-0.106} \text{ J/cm}^2$	-
10^2-on-1	$0.468^{+0.057}_{-0.057} \text{ J/cm}^2$	-
10^3-on-1	$0.468^{+0.057}_{-0.057} \text{ J/cm}^2$	-
10^4-on-1	$0.468^{+0.057}_{-0.057} \text{ J/cm}^2$	-
10^5-on-1	$0.468^{+0.057}_{-0.057} \text{ J/cm}^2$	-
10^6-on-1	$0.412^{+0.049}_{-0.049} \text{ J/cm}^2$	$0.359^{+0.048}_{-0.047} \text{ J/cm}^2$




Figure 2. Characteristic damage curve.