

LIDT TEST RESULTS

LIDT VALUE

10^3 -on-1	$49.4^{+9.3}_{-19.2}$ J/cm ²
--------------	---

CHARACTERISTIC DAMAGE CURVE

Table 1: Estimated LIDTs from fitting model for sample PAN1661_945_1.

Test mode	Threshold (Offline detection - microscopy)	Threshold (Online detection - scattering)
1-on-1	$49.4^{+9.3}_{-19.2}$ J/cm ²	$49.4^{+9.7}_{-19.2}$ J/cm ²
10-on-1	-	$49.4^{+9.7}_{-19.2}$ J/cm ²
10^2 -on-1	-	$49.4^{+9.7}_{-19.2}$ J/cm ²
10^3 -on-1	$49.4^{+9.3}_{-19.2}$ J/cm ²	$49.4^{+9.3}_{-19.2}$ J/cm ²




Figure 2. Characteristic damage curve.